

PAT-NO: JP410321258A

DOCUMENT-IDENTIFIER: JP 10321258 A

TITLE: NONAQUEOUS RECHARGEABLE LITHIUM BATTERY

PUBN-DATE: December 4, 1998

INVENTOR-INFORMATION:

NAME

MAO, HUANYU

DAVID, STANLEY WAINRIGHT

ASSIGNEE-INFORMATION:

NAME

COUNTRY

NEC MOLIERG CANADA LTD

N/A

APPL-NO: JP10127567

APPL-DATE: May 11, 1998

See [0055]

INT-CL (IPC): H01M010/40, H01M002/34, H01M004/58

ABSTRACT:

PROBLEM TO BE SOLVED: To safely release the accumulated energy by overcharge

by adding a monomer for generating a conductive material by polymerization in an electrolyte in overcharge, and automatically internally discharging it when the battery voltage exceeds a maximum operating pressure.

SOLUTION: To an electrolyte is mixed a monomer additive for generating a conductive polymer by polymerization at a battery voltage exceeding a maximum operating voltage and generating an internal short-circuit in the battery. The quantity of the monomer additive must be sufficient for the generated polymer to actually crosslink both a positive electrode and a negative electrode to

short-circuit the battery. A quantity of the monomer additive less than 5 wt.% is sufficient for the mixture of the electrolyte with the monomer additive. As the monomer additive, an aromatic additive can be used. Biphenyl is particularly suitable for a lithium ion type battery having an operating voltage within 4 V, and it is mixed in about 2-3% to the electrolyte mixture.

COPYRIGHT: (C)1998,JPO

(19) 日本国特許庁 (J P)

(12) 公開特許公報 (A)

(11) 特許出願公開番号

特開平10-321258

(43) 公開日 平成10年(1998)12月4日

(51) Int.Cl.⁹

H 0 1 M 10/40

2/34

4/58

識別記号

F I

H 0 1 M 10/40

2/34

4/58

A

A

審査請求 未請求 請求項の数28 O L (全 11 頁)

(21) 出願番号 特願平10-127567

(22) 出願日 平成10年(1998)5月11日

(31) 優先権主張番号 2 2 0 5 8 6 3

(32) 優先日 1997年5月16日

(33) 優先権主張国 カナダ (CA)

(71) 出願人 393000537

エヌイーシーモリエナジー (カナダ) リミ
テッド

カナダ国 プリティッシュコロンビア州
メーブルリッジ市 スチュワート クレッ
セント 20000番地

(72) 発明者 ファニユ マオ

カナダ プリティッシュコロンビア州 メ
ーブルリッジ スチュワート クレッセン
ト 20000 モリ・エナジー (1990) リミ
テッド内

(74) 代理人 弁理士 米澤 明 (外7名)


最終頁に続く

(54) 【発明の名称】 非水系の再充電可能なリチウム電池

(57) 【要約】

【課題】 過充電後に電池内部に蓄積されたエネルギーを安全に放電することができる再充電可能な非水系リチウム電池を得る。

【解決手段】 再充電可能な非水系リチウム電池は、過充電酷使を受けると、比較的危険な充電状態になるため、以降の熱的または機械的酷使において安全面に問題がある。導電性ポリマーを電気化学的に形成する電解質添加剤を使用して、過充電酷使の結果として電池内部に短絡が発生し、電池を内部的に自動放電する。本発明は、電氣的切断装置を設けた電池であって、この切断装置の作動後は外部的に放電できない電池に好適である。ビフェニルなどの芳香族化合物が特に好適な添加剤である。



【特許請求の範囲】

【請求項1】 非水系電解質を有する再充電可能なリチウム電池において、最大動作電圧を超える電池電圧で重合して、導電性ポリマーを生成することによって、過充電酷使時に内部短絡を発生するモノマー添加剤を上記電解質に混合したことを特徴とする非水系の再充電可能なリチウム電池。

【請求項2】 最大動作電圧を超えた場合に、電池を過充電酷使に対して保護する過充電保護手段を有することを特徴とする請求項1に記載の非水系の再充電可能なリチウム電池。

【請求項3】 過充電保護手段が過充電時に抵抗が大きくなることによって充電電流を制限する正の温度係数を持つサーミスタからなることを特徴とする請求項2に記載の非水系の再充電可能なリチウム電池。

【請求項4】 過充電保護手段が所定の内圧で作動する内部電気的切断装置、および過充電時にこの切断装置を作動させる気体および圧力を発生する、前記モノマー以外の気体発生剤からなることを特徴とする請求項2に記載の非水系の再充電可能なリチウム電池。

【請求項5】 気体発生剤が Li_2CO_3 であることを特徴とする請求項4に記載の非水系の再充電可能なリチウム電池。

【請求項6】 過充電保護手段が充電電流または充電電圧を制限する電気回路手段からなることを特徴とする請求項2に記載の非水系の再充電可能なリチウム電池。

【請求項7】 電解質とモノマー添加剤との混合物が5重量%未満のモノマー添加剤を有することを特徴とする請求項1に記載の非水系の再充電可能なリチウム電池。

【請求項8】 モノマー添加剤が芳香族モノマー添加剤であることを特徴とする請求項1に記載の非水系の再充電可能なリチウム電池。

【請求項9】 芳香族モノマー添加剤がビフェニルであることを特徴とする請求項8に記載の非水系の再充電可能なリチウム電池。

【請求項10】 電解質とモノマー添加剤との混合物が2～3重量%のビフェニル添加剤を有することを特徴とする請求項9に記載の非水系の再充電可能なリチウム電池。

【請求項11】 芳香族モノマー添加剤がピロール、N-メチルピロール、チオフェン、フラン、インドール、および3-クロロチオフェンからなる群から選択されるものであることを特徴とする請求項8に記載の非水系の再充電可能なリチウム電池。

【請求項12】 芳香族モノマー添加剤がピロール、N-メチルピロールまたはチオフェンであることを特徴とする請求項8に記載の非水系の再充電可能なリチウム電池。

【請求項13】 芳香族モノマー添加剤がフラン、インドールまたは3-クロロチオフェンであることを特徴と

する請求項8に記載の非水系の再充電可能なリチウム電池。

【請求項14】 最大動作電圧が4ボルトを超えることを特徴とする請求項1に記載の非水系の再充電可能なリチウム電池。

【請求項15】 正極が Li_xCoO_2 、 Li_xNiO_2 または $\text{Li}_x\text{Mn}_2\text{O}_4$ から選ばれるリチウム挿入化合物であることを特徴とする請求項1に記載の非水系の再充電可能なリチウム電池。

10 【請求項16】 負極が炭素質系のリチウム化合物負極である請求項1に記載の非水系の再充電可能なリチウム電池。

【請求項17】 電解質溶剤がエチレンカーボネート、プロピレンカーボネート、ジエチルカーボネート、およびエチルメチルカーボネートからなる群から選択される有機炭酸塩からなることを特徴とする請求項1に記載の非水系の再充電可能なリチウム電池。

20 【請求項18】 電解質の溶剤が LiPF_6 または LiBF_4 であることを特徴とする請求項1に記載の非水系の再充電可能なリチウム電池。

【請求項19】 過充電状態の非水系の再充電可能なリチウム電池を以後の酷使に対して安全にする方法において、

a) 重合して、最大動作電圧を超える電池電圧で導電性ポリマーを形成するモノマー添加剤を選択し、そして
b) 過充電時に重合した添加剤が内部短絡を発生することによって、安全な充電状態まで電池を放電するのに充分な量の上記モノマー添加剤を電解質と混合することからなることを特徴とする過充電状態の非水系の再充電可能なリチウム電池を安全にする方法。

【請求項20】 電解質とモノマー添加剤との混合物が5重量%未満のモノマー添加剤を有することを特徴とする請求項19に記載の方法。

【請求項21】 電解質とモノマー添加剤との混合物が、24時間以内に電池を安全な充電状態まで放電できる内部短絡を発生するのに充分な量でモノマー添加剤を有することを特徴とする請求項19に記載の方法。

【請求項22】 モノマー添加剤が芳香族モノマー添加剤であることを特徴とする請求項19に記載の方法。

40 【請求項23】 上記芳香族モノマー添加剤がビフェニルであることを特徴とする請求項22に記載の方法。

【請求項24】 電解質とモノマー添加剤との混合物が2～3重量%のビフェニル添加剤を含有することを特徴とする請求項23に記載の方法。

【請求項25】 上記芳香族モノマー添加剤がピロール、N-メチルピロール、チオフェン、フラン、インドール、および3-クロロチオフェンからなる群から選択されるものであることを特徴とする請求項22に記載の方法。

50 【請求項26】 上記芳香族モノマー添加剤がピロー

ル、N-メチルピロールまたはチオフェンであることを特徴とする請求項22に記載の方法。

【請求項27】 上記芳香族モノマー添加剤がフラン、インドールまたは3-クロロチオフェンであることを特徴とする請求項22に記載の方法。

【請求項28】 上記最大動作電圧が4ボルトを超える請求項19に記載の方法。

【発明の詳細な説明】

【0001】

【発明の属する技術分野】本発明は非水系の再充電可能なリチウム電池、およびその安全性の改善方法に関する。特に、本発明は、リチウムイオン電池の過充電後にさらなる酷使に対するリチウムイオン電池の安全対策として重合性モノマー添加剤を使用することに関する。

【0002】

【従来の技術】かつてない程エネルギー密度の高い再充電可能な電池が求められている結果、再充電可能なリチウム電池に関する研究や開発が盛んになっている。リチウムを使用すると、高エネルギー密度、高電池電圧、また長い貯蔵寿命が得られるが、安全性の問題（即ち、火災）が生じる。というのは、リチウムは反応性の高い元素であるためである。このように安全性に問題があるため、多くの再充電可能なリチウム電池は、その電気化学的作用及び／又はサイズが一般的な使用には向いていない。一般的にいて、リチウム金属単体からなる、あるいはリチウム合金からなる負極を利用する電気化学作用の電池が一般に利用できるのは、極めて小形のもの（例えば、大きさがコイン程度の電池）か一次電池（すなわち、再充電できない電池）である。しかし、このような電気化学作用をもつ大形の再充電可能な電池は、安全面がそれ程重視されてない、軍事用途やある主の遠隔地での給電用途には使用できる。

【0003】最近、リチウムイオン形または「ロッキングチェア形」として知られている再充電可能なリチウム電池が市販されるようになってきている。これら電池は、多くの消費者エレクトロニクス用途にとって好適な再充電可能な電力源になっている。現在利用できる従来形の再充電可能な電池（即ち、Ni-Cd電池、Ni-MH電池、または鉛酸電池）の中でも、これら電池は最大のエネルギー密度（Wh/L）をもっている。さらに、リチウムイオン形電池の動作電圧は十分高く、多くのエレクトロニクス用途では、1個の電池で十分その役割を果たすことができる。

【0004】リチウムイオン形電池の場合、活性正極および負極に対して2種類の異なる挿入化合物を使用する。LiCoO₂/黒鉛前駆体炭素の電気化学作用に基づく3.6V（平均）のリチウム電池は現在市販されている。また、これ以外にも、LiNiO₂やLiMn₂O₄を始めとする多数のリチウム遷移金属酸化物化合物も正極材料として使用するのに好適である。また、コー

クスや純粋な黒鉛を始めとする広範囲にわたる炭素質系化合物も負極材料として使用するのに好適である。上記電池製品では、LiBF₄塩やLiPF₆塩、およびエチレンカーボネート、プロピレンカーボネート、ジエチルカーボネートやエチルメチルカーボネートなどの溶剤混合物からなる非水系電解質を使用している。同様に、これら電池に使用する塩及び／又は溶剤については数多くの選択肢が存在していることが知られている。

【0005】リチウムイオン形電池は、ある種の酷使、特に再充電時に通常の動作電圧を上回るような過充電酷使には弱い。過充電時、正極から過剰なリチウムが抽出され、これに対応して負極ではリチウムの過剰な挿入、場合によってはめっきが生じる。この結果、両電極の熱安定性が劣化する。負極は反応性リチウムでドーピングまたはめっきされると安定性が低下する傾向があり、一方正極の場合は、分解して、酸素を発生する傾向が強くなる（J.R.Dahn et al., Solid State Ionics, 69(3-4), p 265-270, 1994を参照）。また、過充電の結果、電池の加熱が生じることもある。というのは、入力したエネルギーの多くは蓄積されるというよりは、放散されるからである。熱安定性の低下が電池の加熱とともに生じると、過充電時に危険な熱的暴走が生じ、火災が発生する恐れがある。

【0006】一般に、個々のリチウムイオン形電池の集成体からなる電池充電装置及び／又は電池パックは過充電を防止する適当な電気回路を備えている。ところが、回路の万一の故障に対処するため、多くのメーカーは、過充電酷使に対する保護レベルを上げる手段として別に安全装置を個々の電池自体に組み込んでいる。例えば、それぞれ米国特許明細書第4943497号や1993年6月25日に出願され、1994年2月11日に公開されたカナダ特許出願第2,099,657号明細書に記載されているように、ソニー社やMoli Energy（1990）Limited社が現在製造している製品は、過充電酷使時に電池の内圧がある所定の値を越えたときに作動する切断装置を内部に組み込んである。また、過充電時にある所定の電圧を超えたときに十分な気体を発生して、切断装置を作動させるために、各種の気体発生剤（例えば、正極化合物及び／又は他の電池添加剤）も使用することができる。

【0007】別な代替方法では、内部固体容積を実質的に大きくして、特定の過充電状態になった時に切断装置を液圧により作動させるようにしている（これについては、1993年4月8日に出願され、1994年10月9日に公開されたカナダ特許出願第2,093,763号明細書に開示がある）。

【0008】他の過充電安全装置をリチウム電池それ自体に組み込んで、充電電流及び／又は電圧を制限することも可能である。一部の製造業者では、正の温度係数のサーミスタ（PTC）を組み込んで、過充電酷使時の充

電流を部分的に制限している。この装置の場合、電池の加熱とPTCのIR加熱との組み合わせを使用して、PTCを作動することによって、抵抗を大きくし、充電電流を制限している。原則的には、個々の電池それ自体のヘッダーに過充電保護用電気回路を組み込むことも考慮の対象とすることができる。

【0009】これらの付加的な、あるいは予備的な安全装置は、過充電の電氣的酷使により生じる危険な問題を解消する限りでは、有効な装置といえるが、過充電電池の場合、充電状態は通常より高くなっている。従って、電池構成体の熱的安定性が正常時より低く、正常時より危険な状態になっている。このような過充電状態にある電池は、次の機械的な酷使（例えば、破壊）や熱的酷使（例えば、オープン加熱）に非常に弱い。大多数の電池の場合、過充電酷使が生じたならば、手作業で単に放電することによって安全な放電状態にしてから廃棄するようにしているが、この放電を自動化することが好ましい。

【0010】ところが、内部電氣的切断装置が作動状態にある電池は、外部から放電して、エネルギーを取り去り、充電状態を低くすることができない。このような切断状態にある電池は、異常な程危険な状態にあり、廃棄したり、あるいは突き固めるさいに別な問題を発生する。不幸なことだが、いったん切断すると、このような電池は残存容量がなくなっている（すなわち、完全に電池が作動しない状態になっている）はずと考えられている。この時点で、軽率な消費者ならば、電池を解体したり、あるいは機械的に乱暴に扱う誘惑に負ける恐れが通常よりも大きくなるが、不幸な結果になることがある。即ち、このような過充電状態にある電池を自動的に、かつ内部的に放電する手段が強く求められている。

【0011】電池を自動的に放電するいくつかの手段は公知であり、既に提案されている。電気化学作用の水系電池の場合、充電の最後で再結合反応が生じる。この再結合反応が有効に作用して、充電が継続している間電池を連続放電する。同じような目的をもつ電気化学作用の非水系電池についても、添加剤（化学的シャトル）が開示されている。再結合反応および化学的シャトルは、通常の最大動作充電電圧を越えない限りにおいてという前提でのみ、電池を自動放電するものとみなすことができる。

【0012】過充電電池に内部短絡を発生する手段も公知である。電気化学的腐食反応を利用して、正極電位に維持される金属部品（例えば、正極集電体）や他の添加剤を急激に腐食することができる。この場合、腐食した成分が正極から移動して、負極をめっきする結果、導電性デンドライトが生成する。腐食およびめっきが続くと、正極と負極との間に導電性デンドライトの架橋が形成し、このデンドライトの架橋によって電池を電氣的に短絡できる。デンドライトの架橋が形成するまでは、腐

食反応において電池容量がほとんど消費されないことが多い。従って、最大動作電圧以上で腐食が開始し、そして過充電が安全を脅かす前にかかなりの腐食が生じる場合には、上記目的に正極金属部品やその他の添加剤が好適に使用することができる。低電圧（例えば、約2ボルト）の非水系電池については、容易に利用できる材料の選択肢が数多く存在する。例えば、1980年代にMoli Energy Ltd が製造していたリチウム負極/二硫化モリブデン正極電池の場合、負極電位にあるステンレス鋼及び/又はニッケル金属部品が腐食し、デンドライトの架橋を形成し、電池を内部的に短絡することによって、充電状態を制限するとともに、過充電酷使時に電池を保護するようになっていた。しかし、より高い電圧（例えば、約4ボルト）の非水系電池にはそれ程多くの選択肢は存在しない。現在利用されている電池金属材料の多くは、電池の正常な動作を確保するために、あまりにも低い電位で腐食する。一方、あまりにも低い電位では腐食しない特殊材料は、過充電保護が必要な場合には十分に腐食しない。このように、通常材料や特殊材料のいずれもより高い電圧の非水系電池に簡単には利用できない。

【0013】過充電電池に内部短絡を発生する機械的手段も検討されている。例えば、提案されている一つの選択肢は、作動時に切断を行なう代わりに、短絡接続を行なう機構を組み込んだ点を除けば、上記電氣的切断装置と同じである。しかし、この選択肢は機械的に複雑であり、コストや信頼性に問題がある。理想をいえば、過充電時に内部短絡を行なう手段は信頼性が高く、コストが低くなければならない。また、最適には、徐々に段階的に程度の低い短絡を発生し、場合に応じて電池内部全体に配分して、短絡を通じて放散されるパワーおよび熱が突然大きくならないように、あるいは局部化（即ち、スポット加熱の発生）しないようにする。これら後者の条件はいずれもそれ自体が危険である。

【0014】本出願人が1995年11月17日に出願したカナダ特許出願第2,163,187号明細書（特開平9-171840号公報）には、過充電時に内部電氣的切断装置を作動する目的で、リチウム電池に気体発生剤などの重合性モノマー添加剤を使用することが開示されている。この明細書には、導電性ポリマーを生成するある種のモノマー気体発生剤は内部短絡を発生し、過充電酷使後に電池を放電する作用を併せもつことも開示されている。実施例によれば、この作用は、実際には、ビフェニル添加剤を配合した電池により得られる。ビフェニルの重合体は導電性である。

【0015】また、本出願人が1995年8月23日に出願したカナダ特許出願第2,156,800号明細書（特開平9-106835号公報）には、過充電の間、再充電可能なリチウム電池を保護する目的で、重合性モノマー添加剤を使用することが開示されている。ここで

は、液体電解質に少量の重合性添加剤を混合する。過充電時、電池の最大動作電圧を超える電圧で芳香族添加剤が重合することによって、内部抵抗を大きくして、十分な保護を与える。

【0016】上記のカナダ特許出願第2,163,187号明細書および同2,156,800号明細書のいずれにも、電池に内部切断装置を組み込んであるかどうかに関係なく、一般的に、過充電酷使後に、電池自体を自動的に放電するようにすることが有利であることは直接的に開示されていない。また、重合した時に導電性重合体を生成するモノマー添加剤が気体発生剤であるか、あるいは電池の内部抵抗をかなり大きくするかに関係なく、モノマー添加剤を使用することが有利であることについても、直接的な開示はない。

【0017】基本的に、電気化学的に重合して、導電性ポリマーを生成できるいくつかの芳香族化合物が、サイクル寿命を延長するために、電解質溶剤混合物に、塩及び／又はある種の再充電可能な非水系リチウム電池の電解質溶剤添加剤として既に使用されている。特開昭61-230276号公報では、フラン（芳香族複素環）溶剤添加剤からなる電解質を使用する実験室試験用電池が、めっきしたリチウム金属についてはサイクル効率を改善することが確認されている。また、特開昭61-147475号公報には、負極をポリアセチレンとし、正極を TiS_2 とし、チオフェン溶剤添加剤からなる電解質を使用した電池が、添加剤を使用しない以外は同様な電池と比較した場合、サイクル特性においてすぐれていることが示されている。しかし、これら公報には、添加剤の電気化学的重合性から得られる潜在的な安全面における作用についてはなにも開示がない。また、これら公報における実際の実施態様が、過充電酷使時に現実的な安全面における作用をもつかどうか、（即ち過充電時に生じる他の作用が重合性を阻止するのか、及び／又は重合の結果として内部短絡が生じないのか）明確ではない。

【0018】

【発明が解決しようとする課題】本発明は非水系の再充電可能なリチウム電池において、過充電酷使後に、充電された電池容量を内部で放電し、電池を安全なものとするを課題とするものである。

【0019】

【課題を解決するための手段】本発明は、再充電可能な非水系リチウム電池の過充電酷使後に、この電池を自動的に内部放電する方法および実施態様の両者に関するものである。（この場合、過充電酷使とは、通常の最大動作充電電圧を超える電圧まで電池を充電した場合に生じるものとする）。重合すると、導電性重合体を生成するモノマー添加剤を非水系電解質に配合する。過充電酷使時に、このモノマー添加剤が重合することによって、電池に内部短絡を発生し、これを放電する。

【0020】本発明は、過充電保護手段を個々に追加する必要がある電池に、またはその必要のない電池のいずれに対しても有効である。例えば、低電圧電池の場合、電気的過充電酷使に対する安全を保障する追加的な手段は必要ないかもしれないが、このような低電圧電池でも、過充電後には、次の熱的酷使において安全を脅かす恐れがある。このため、本発明は、これら低電圧電池をより低い充電状態に放電して、次の熱的酷使における安全性を高くする場合にも有効である。

【0021】同様に、本発明は、充電電流または電圧を制限するために、正の温度係数を有するサーミスタ（PTC）やその他の電気回路手段を備えた電池にも有効である。このような電池の場合、例えば、制御された速度で手作業により放電して、安全性を必要に応じて高くすることができる。しかし、安全面からみた場合、放電を確実にこなうためには、この放電を自動的かつ内部的に行なうのが好ましい。ビフェニルなどの本発明のある種の添加剤の場合、過充電状態のPTCを備えた電池を自動的に放電できるだけでなく、（前記カナダ特許出願第2,156,800号明細書に開示されているように）内部インピーダンスを大きくすることによって過充電時にPTCの作用を高めることもできる。

【0022】本発明は、所定の内部圧力で作動する内部電気的切断装置を備えた再充電可能なリチウム電池に適用するのが好ましい。前記カナダ特許出願第2,163,187号と同様に、モノマー添加剤は活性化気体発生剤として作用するとともに、重合した時に内部短絡を発生するモノマーとして作用する。しかしながら、本発明のモノマー添加剤は圧力活性化気体の一次源である必要はなく、気体発生剤である必要はない。このような実施態様の場合には、電気的切断装置を作動する他の手段を本発明のモノマー添加剤と組み合わせて使用するのが望ましい。部分的な過充電後に、（即ち、電気的切断装置の作動前に過充電が停止した後に）本発明の添加剤によって内部短絡を発生できるため、過充電電池を放電でき、また過充電酷使が生じていることが切断装置の作動によってわかった場合にも過充電電池を安全なものにすることができる。

【0023】一般に、本発明の再充電可能な非水系電池はリチウム挿入化合物正極、リチウム化合物負極（例えば、リチウム金属、リチウム合金あるいはリチウム挿入化合物）、および非水系電解質（例えば、液状電解質であるが、高分子電解質や可塑化高分子電解質も使用可能である）で構成するものである。リチウムイオン電池の場合、リチウム挿入化合物としては、 Li_xCoO_2 が使用でき、また Li_xNiO_2 及び $Li_xMn_2O_4$ からなる群から選択したものも使用できる。リチウム化合物負極には、炭素質系挿入化合物が使用できる。液体電解質溶剤としては、エチレンカーボネート、プロピレンカーボネート、ジエチルカーボネートやエチルメチル

カーボネートなどの有機炭酸塩が使用できる。液体電解質溶質としては、 LiPF_6 や LiBF_4 などのリチウム塩が使用できる。特に、本発明は最大動作充電電圧が4ボルトを超える電池に好適である。

【0024】本発明の電池では、最大動作電圧を超える電池電圧で重合することによって、導電性ポリマーを生成し、電池に内部短絡を発生するモノマー添加剤を電解質に混合する。モノマー添加剤の量については、生成したポリマーが実際に正極および負極両者を架橋して、電池を短絡するのに十分でなければならない。電解質とモノマー添加剤との混合物においてモノマー添加剤の量が5重量%未満であれば十分である。モノマー添加剤としては、芳香族添加剤が使用できる。ビフェニルが、動作電圧が4ボルト範囲にあるリチウムイオン形電池に特に好適な添加剤である。ビフェニルは、電解質混合物中に約2〜3重量%の量で配合すれば効果がある。

【0025】芳香族複素環式化合物も添加剤として好適である。例えば、ピロール、N-メチルピロール、チオフェンなどが重合すると、ある種の電池に内部短絡を発生する。このように広くいえば、これら添加剤は潜在的に好適な添加剤であるが、好ましい対象電池は最大動作充電電圧が約4ボルト未満の電池である。フラン、インドール、3-クロロチオフェンなどの添加剤は、動作充電電圧がより高い電池を対象とする潜在的に好適な添加剤である。これら化合物中の異なる化学基を置換しても、生成するポリマーの重合電位及び／又は導電性に若干の影響がでるだけと考えられる。即ち、これら置換化合物も好適な及び／又は好ましい添加剤である。

【0026】ある電池を対象として所期の結果を得る方法では、最大動作充電電圧を超える電池電圧で導電性ポリマーを重合により生成するモノマー添加剤を選択し、過充電酷使時に重合添加剤が内部短絡を発生することによって、安全な充電状態まで電池を自動放電するのに十分な量のモノマー添加剤を電解質と混合する。あまりにも速すぎる放電速度やあまりにも遅すぎる放電速度のいずれも望ましくなく、また添加剤には他の目的がないので、発生した内部短絡によって約24時間以内で安全な充電状態に電池を放電できる限り、最少量の添加剤を使用するのが好ましい。(もちろん、ビフェニルなどの添加剤には別な有効な作用がある。例えば、前記2件のカナダ特許出願第2,156,800号および第2,163,189号明細書に記載されているように、切断装置を作動したり、電池インピーダンスを大きくする作用をもつ)。

【0027】

【発明の実施の形態】なんらかのエネルギー保存装置の場合、事故を最小限に抑えるために、その使用時期の最後で、廃棄に先立ち、あるいは場合によって電池を酷使するなんらかの処理に先立ち、エネルギーを取り去っておくのが理想である。再充電可能な非水系電池、特に一

般消費者向けの電池も例外ではない。一般に利用されている非水系電気化学装置の大半は過剰充電に対して保護が必要である。というのは、このような過剰充電が生じると、通常は、電池にエネルギーが完全充填された時に望ましくない反応生成物や副生熱が生じるからである。これら電池は過充電自体に対しては十分に保護されているが、その後再度酷使(「積み重ね」酷使として知られている)されると、安全を潜在的に脅かすものとなる。

【0028】安全を確保するために、一般の人々の自発的行動に頼ることは好ましくない。電池パックについては、一般の人々が解体することによって外部保護装置を取り外したりすることがある。同時に、あるいは、警告書にもかかわらず、またそのように扱った際の危険が周知されているにもかかわらず、個々の電池が酷使されることがある。寿命が若干残っている電池よりも動作不能電池のほうが、一般の人々によってなんの注意もなく扱われる恐れが強い。この点で、動作不能電池自体を過充電後に安全な放電速度で自動放電できるならば、消費者に頼る必要を望ましくは回避できる。

【0029】リチウムイオン形電池は、一般に、充電状態が増大するに従って、熱的酷使に対する安定性が低くなる傾向がある。ある種の市販リチウムイオン形電池の場合、一つは電池を比較的安全な充電状態に熱的に制限する目的で、上限電圧が指定されている。他の形式の電池と比較した場合、基本的に、このようなリチウムイオン形電池が過充電状態になると、電池内部圧力の増大による圧力開放や火災が発生する恐れが強い。このため、例えば、リチウムイオン形電池及び／又は電池パックには、過充電を防止するために、信頼性のある外部回路を設ける。ところが、この外部回路はユーザーがその気になれば外すことができるものであり、信頼性の最も高い回路ですら、破損率は小さいが限界はある。従って、市販のリチウムイオン形電池には、専ら内部過充電保護装置が設けられている。これら装置は、例えば外部装置が外されたり、あるいは破損した場合でも保護を与えるのに有効である。

【0030】リチウムイオン形電池の場合、内部過充電保護装置がいったん作動したならば、使用不能状態になるのが好ましい。放電されるまで、過充電電池は次の熱的または機械的酷使に対して安全を潜在的に脅かすものであり続ける。不幸にも、その後の放電を行なうためには、ユーザーが適宜介入する必要がたびたび生じる。場合にもよるが、ユーザーが電池を外部的に放電できないことすらある。これは内部の電氣的切断装置が作動した場合にもあてはまる。切断装置が作動した電池は、ユーザーにとっては、「死んだ」状態の電池であり、外部からは放電できない電池である。

【0031】本発明はこの問題に取り組むために、非水系電池の過充電後に電池を自動放電する手段を提供するものである。これは、電池の非水系電解質に好適な重合

性モノマー添加剤を少量配合することによって実現する。このモノマー添加剤については、ある適当な電圧で重合して、導電性ポリマーになるものを選択すればよい。換言すれば、電池の正常動作時に（即ち、正常な動作電圧範囲では）、有意な重合が起きないモノマーを選択すればよい。モノマー添加剤は、過充電酷使時に、重合電圧に達すると、重合を開始する。最終的に、十分な導電性ポリマーが生成して、電池電極間に導電性の架橋を形成することによって、電池に内部短絡を発生し、電池を放電する。安全面からみた場合、電池が望ましくない充電状態に達する前に、導電性の架橋が形成しているのが好ましい。こうしておけば、内部放電の開始がない限り、電池が部分的に上記の望ましくない状態に過充電されることはありえない。

【0032】従って、モノマー添加剤は、有効であるためには、いくつかの条件を同時に満足する必要がある。即ち、電気化学的に重合して、むしろ特定の電圧で導電性ポリマーの架橋を形成できなければならない。また、この点を除いて、添加剤の配合が電池性能に悪影響を与えてはならない。原則的には、多くのモノマーを使用することができるが、芳香族モノマーが特に好適である。というのは、重合電位がこの用途に適する範囲にあるうに、重合反応により導電性ポリマーが生成するからである。さらに、芳香族化合物には、少量でも、リチウム電池の化学作用に適合性を示すことが多いという利点もある。

【0033】1979年に Willard Grant Press社から発行された、R.J.Fessenden et al.を著者とする "Organic Chemistry" で議論されているように、用語「芳香族」とは、 π 電子の非局在化によって実質的に安定化される環式化合物を指すものである。このような化合物*

化合物	酸化電位 (V対SCE)	導電率 (Scm^{-1})
ピロール	+0.8	30-100
インドール	+0.8	5×10^{-3} - 10^{-2}
チオフェン	+0.9	10-100
フラン	+1.85	10-80

【0037】なお、重合電位は、ある程度は、電極および電気化学的装置（電池）に使用する他の電解質成分に依存するものである。文献に記載されている値は、本発明が対象とする用途において候補となり得る化合物を示唆するものであるが、実際の電池環境ではいくぶん異なった形で重合が進行する。即ち、電池最大動作充電電圧を超えるが、実際の電池条件下では電池が安全を比較的脅かすものになる過充電電圧を下回る電圧で重合する化合物が好適である。なお、重合については、必要になる時点までに十分なポリマーにより十分な架橋を形成するのに十分な重合速度が必要である。

【0038】重合体に必要な導電性は、ある程度は、重合体の形態および電池の電気化学作用および電池設計に依存するものである。緻密なポリマーの導電性の架橋は※50

*は環構造か平面構造をもち、環の各原子は環の平面に対して直交するp軌道をもつ (sp^2 混成状態)。また、環系には $4n+2$ 個の π 電子 (n は整数である) が存在しなければならない (ヒュッケル則)。用語「複素環式」とは、(The Condensed Chemical Dictionary, 第9版, G. G. Hawley, Van Nostrand Reinhold, 1977年参照)、通常は5員か6員の閉環構造を指すものである。この場合、環中の一つかそれ以上の原子は炭素以外の元素 (例えば、硫黄、酸素や窒素) である。

【0034】一般的な芳香族化合物は、本発明が対象とする用途における電圧範囲で電気化学的にきわめて容易に重合できる環構造をもつ。多くの芳香族複素環式化合物の場合、その環構造に異種原子が存在すると、これに隣接する炭素原子が電子に富んだ状態になるため、簡単に開環が生じ、これらの位置で重合が生じる。他の不飽和環式化合物の場合、これ程簡単には電気化学重合しない。

【0035】導電性ポリマーを生成する芳香族化合物としては、例えば、ビフェニル、ピロール、インドール、チオフェン、フランやこれらの誘導体などが使用できる。(Electrochemistry in Organic Synthesis, J. Volke & F. Liska, Springer-Verlag, 1994から再録した) 表1に、いくつかのモノマーの飽和甘汞電極に対する酸化電位と形成したポリマーフィルムの導電性を示す。

【0036】

【表1】

※繊維性の強い架橋よりも抵抗が低いと考えられる。セパレータが厚く、及び/又は電極面積が小さい電池の場合、セパレータが薄く、及び/又は電極面積が大きい電池よりも導電性の高いポリマーが必要である。というのは、抵抗の高いポリマーの場合、同じ実抵抗を得るために、架橋体を短くし、横断面積を大きくできるからである。最後に、必要な内部抵抗は特定の電池電圧、容量、および充電状態に対する安全基準を依存するものである。

【0039】一般的にいつて、本発明の目的からは、所期の内部短絡を得る最少量のモノマー添加剤を使用すればよい。添加剤は、まず第1にリチウムに対して、そして電極に対して比較的不活性でなければならないが (即ち、リチウムと反応したり、電極に挿入することはあつ

てはならないが)、不活性であっても添加剤を過剰な量で使用すると、(例えば電池インピーダンスの増加によって)電池性能特性に悪影響を与えることがある。代表例の挙げれば、本発明においては、電解質に数重量%か数容量%で添加剤が存在すればそれで充分である。実際に使用可能な必要量は、同様に、一部は電池の電気化学作用および電池設計、そして一部はモノマー特性に依存するものである。

【0040】用途に応じて添加剤を選択するには、従って、いくつかの基準を満足する必要がある。これら基準を満足する許容範囲は比較的広いが、所定の電池用途に対して候補となる特定の添加剤の適合性を知るために、発明には直接関係のない実験をいくつか行なう必要がある。これら実験には、候補となる添加剤を異なる量で含有する試作電池の過充電試験がある。表面的には使用可能な量の添加剤を選択するさいに、あるいは選択した後に、性能に対する悪影響を完全に試験するために、試作電池についてある種の性能試験を行なう必要がある。このような試作電池は当業者の範囲および能力範囲にあり、別に発明性を必要としない。

【0041】発明者等は、消費者エレクトロニクスを対象として市販されているリチウムイオン形電池製品に特に好適な添加剤はビフェニルであることを見いだした。これら電池は、例えば、セパレータが薄く(約25 μ m)、電極表面積が大きい(約数百 cm^2)である。電池容量については、1Ahかそれ以上であるのが普通である。また、正常な最大動作充電電圧は約4.2Vである。この4.2Vと約5Vとの間で、電池の危険性が比較強くなる。Cレート以上で放電が生じると、数%のビフェニルが十分に重合して、導電性の架橋を形成し、24時間以内で電池を安全な充電状態まで放電する。カナダ特許出願第2,156,800号明細書に開示されているように、このような電池環境においては、ビフェニル添加剤は Li^-/Li^+ に対して4.70Vで重合すると考えられ、少量の使用では、電池性能に有意な悪影響を与えない。同明細書では、3-クロロチオフェンやフランなどの他の潜在的に好適な添加剤も使用可能であるとされている。

【0042】後述する実施例によって、他の添加剤も、より低い動作充電電圧(即ち、4.2V未満)をもつ非水系電池に好適であることが判明した。これら添加剤には、N-メチルピロールやチオフェンがあり、電圧がより低い電池により好適であると考えられる。というのは、代表的な電池ではあまりにも低い電圧で内部短絡が発生するからである。上記添加剤と密接な関係がある他の添加剤(即ち、置換化合物やその誘導体)も同様ではあるがわずかに異なる特性を示し、それ故ある種の用途における好ましい選択肢であると考えられる。

【0043】添加剤の存在を別にすれば、本発明電池の構成は従来電池と同様である。一般的には、電池組み立

て時のある好適な時点で、使用可能量の添加剤をバルク電解質に単に混合するだけでよい。いうまでもなく、バルク電解質や添加剤の特性(例えば、蒸気圧、毒性など)の違いに応じて多少の操作上の変更が必要である。市販されている非水系の再充電可能なリチウム電池は各種の形状(即ち、角柱状電池や小形のコイン形電池)をもち、多くの異なる成分を使用することができる。(例えば、このような添加剤は恐らく高分子系電解質においてあまり移動しないが、固体高分子電解質からなる電池も、このような添加剤を配合することによって同様な特性を実現する)。リチウムイオン形電池製品の好ましい構成については、図1に従来の螺旋状電池として横断面図を示す。正極箔1、負極箔2、およびセパレータとして作用する、2枚の微孔性ポリオレフィンシート3を螺旋巻きにしてジェリーロール4を作製する。

【0044】正極箔は、薄いアルミニウム箔に、リチウム化遷移金属酸化物などの適当な粉末状(粒度が例えば約10 μ m)正極材料、所望ならば他の粉末状正極材料、結合剤、および導電性希釈剤からなる混合物を塗布して作製する。塗布方法の代表例では、まず、適当な液体担体に結合剤を溶解してから、この溶液に加えて他の粉末状固体成分を使用して、スラリーを作製する。次に、基体箔に均一にスラリーを塗布する。その後、担体溶剤を蒸発除去する。多くの場合、このようにしてアルミニウム箔基体の両側を塗布処理してから、正極箔をカレンダー処理する。

【0045】負極箔の場合は、正極材料の代わりに粉末状(粒度が例えば約10 μ m)の炭素質系挿入化合物を使用し、そして通常はアルミニウムの代わりに薄い銅箔を使用する以外は、上記と同様にして作製する。また、負極箔の幅を正極箔の幅よりわずかに広くして、負極箔が常に正極箔に確実に対向するようにする。

【0046】ジェリーロール4を通常の電池缶10に挿入する。ヘッダー11およびガスケット12を使用して、電池15を密封する。ヘッダー11の外面を正端子として、そして電槽10の外面を負端子として使用する。正極タブ6および負極タブ7を適当に接続して、内部電極と外部端子を接続する。適当な絶縁片8および9を挿入して、内部短絡の可能性を未然に防止することができる。ヘッダー11を電池缶10にクリンプして、電池を密封する前に、電解質5を加えて、ジェリーロール4の微孔空間を充填する。本発明の電池の場合、使用可能量のモノマー添加剤をさらに電解質5に配合する。例えば、圧力動作式内部電氣的切断装置、正の熱係数サーミスタ(PTC)や過充電保護装置などの一つかそれ以上の装置を設けて、電池を過充電による電氣的酷使から保護する。また、別な理由から、安全装置をヘッダーに組み込んでもよい。通常、電池に過剰な圧力が蓄積した場合に破裂する安全口を組み込んでおいても良い。

【0047】また、図1に示した電池では、カナダ特許

出願第2,099,657号明細書に示されているのと同様な内部電氣的切断装置をヘッダー11に組み込む。この切断装置は、 Li_2CO_3 などの気体発生剤によって作動できる。この気体発生剤は、(上記カナダ特許出願第2,163,187号明細書に示されているように)、内部短絡を発生する重合性添加剤としても使用できるが、これは必ずしも必要ではない。あるいは、内部短絡を発生する、過充電時に気体を発生しない重合性添加剤を使用したり、切断装置を作動するために別な手段(例えば、上記カナダ特許出願第2,093,763号明細書に開示されている手段)を使用することも好ましい。2重結合の破断によって重合するモノマー添加剤は気体状副産物を発生することがないので、このような場合に好適である。

【0048】以下、例示のみを目的として説明を続けるが、どのような意味でも本発明を制限するものではない。理論の制限を受けるものではないが、添加剤の重合は正極で生じ、正極表面にポリマーを生成するものと考えられる。電解質に入った添加剤は、正極に向かって移動を続け、正極に接触して重合し、最終的にセパレータを介して負極に接触する析出物が成長する。このようにして、導電性の架橋が形成できる。代表的なリチウムイオン形電池の場合、電極はいずれも薄く、低容量の微孔性セパレータに物理的に接触している。従って、比較的少量のモノマーでも所期の内部短絡を実現できると考えられる。

【0049】

【実施例】以下、実施例によって本発明のいくつかの態様を説明するが、これら実施例はどのような意味においても本発明を制限するものではない。既に説明し、かつ全体を図1に示すように、18650サイズ(直径が18mmで、高さが65mm)の円筒形電池を作製した。正極1は幅が約5.4cmで、長さが約49.5cmの薄いアルミニウム箔の両側に LiCoO_2 粉末、炭素質系導電性希釈剤及びポリフッ化ビニリデン(PVDF)結合剤からなる混合物を均一に塗布して作製した。塗布量は約47mg/cm²であった。負極2については、長さが正極と同じであるが、幅が3mm広い薄い銅箔に、球状黒鉛粉末、カーボンブラックSuperS(Ensagri社の商標)およびポリフッ化ビニリデン(PVDF)結合剤(球状黒鉛粉末に対してそれぞれ約2重量%および約10重量%の量で使用)からなる混合物を均一に塗布して作製した。塗布量は約23mg/cm²であった。微孔性ポリプロピレン膜を使用してセパレータ3を作製した。電解質5として、EC/PC/D EC容量比が30/20/50のエチレンカーボネート(EC)、プロピレンカーボネート(PC)、およびジエチルカーボネート(DEC)からなる溶剤混合物に溶解したリチウム塩の溶液を使用した。各電池にほぼ5m lの電解質を使用した。

【0050】実施例1

1.5Mの LiBF_4 を使用し、上記のようにして18650型の電池を2個組み立てた。ただし、第1の比較用電池には添加剤を使用せず、第2の本発明電池には電解質に2重量%のビフェニル添加剤を配合した。(なお、ビフェニルは室温で固体であるため、便宜上容量ではなく、重量で定量化する)。これら電池には、上記カナダ特許出願第2,099,657号明細書に記載されているように、圧力開放口および内部電氣的切断装置を設けた。充電、放電、次に4.1ボルトの正常最大動作充電電圧まで再充電することによって電池をまず21℃で状態調節した。

【0051】10ボルトの供給能力を持つ給電装置を使用して、21℃の周囲温度で上記2個の電池を過充電試験した。それぞれ3A及び3.6Aで電池を12分間(内部電氣的切断装置が作動することなく電池の充電状態を有意に高くできるのに十分な時間)部分的に過充電した。次に、電池を約19時間モニターした。この間、第1の電池の電圧は約4.5ボルトで安定していた。第2の電池の電圧は連続的に降下し、19時間後に約4.05ボルトになった。各電池につき爪貫入試験を行なったところ、内部短絡が生じた。第1の比較用電池は圧力開放口が動作して爆発し、発炎した。本実施例は、ビフェニル添加剤を配合した電池は、比較用電池と比較した場合、最初に僅かに高く過充電状態にあったにもかかわらず、それ自身が十分に放電したので、後の機械的酷使時における安全性が著しく高かったことを示す。

【0052】実施例2

a) 2.5重量%のビフェニル添加剤を配合した1Mの LiPF_6 電解質溶液を使用した以外は、実施例1と同様にして10個の18650型電池を組み立て、状態調節した。内部電氣的切断装置が作動するまで、21℃、3.6Aで電池を過充電した。(本実施例では、ビフェニルは気体発生剤としても作用し、上記カナダ特許第2,163,187号明細書に記載されているように、切断装置を作動した)。電池を24時間保存してから、爪貫入試験を行なった。電池の圧力開放口の開放もなく、燃焼もなかった。爪貫入試験中に電池に記録された最高表面温度は33℃であった。

【0053】b) 添加剤および内部切断装置のいずれも使用しなかった点を除いて、a)と同様にして3個の18650型電池を組み立て、状態調節した。ただし、これら電池のヘッダーにはPTC装置を組み込み、充電電流を制限することによって、過充電酷使に対して電池を保護した。PTCが作動するまで(即ち、PTCが十分に加熱して、抵抗が急激かつ著しく上昇するまで)、21℃、3.6Aでこれら電池を過充電した。圧力開放口の開放もなく、燃焼もなかった。次に、電池を24時間開路状態で保存してから、爪貫入試験した。これら3つ

の電池のうち一つが電池漏れが激しく、発炎した。

【0054】c) 添加剤を配合しない、1.5MのLiBF₄電解質溶液を使用した点を除いて、上記と同様にして、6個の18650型電池を組み立て、状態調節した。上記カナダ特許出願第2,093,763号明細書に記載されているように、ある特定の過充電状態における内部固体容量の増加により内部電氣的切断装置が液圧作動するように、各電池を構成した。内部電氣的切断装置が作動するまで、21℃、3.6Aでこれら電池を過充電した。電池漏れもなく、燃焼もなかった。次に、電池を24時間保存してから、爪貫入試験した。これら6個の電池のうち5個が電池漏れが激しく、発炎した。本実施例は、過充電後24時間以内に、添加剤を配合し、切断装置を備えた電池の場合、切断装置またはPTCのいずれかを備えるが、添加剤は配合していない比較用電池に比べて、次の機械的酷使における安全性が著しく高くなったことを示す。

【0055】実施例3

5重量%のビフェニル添加剤を電解質に配合した以外は、実施例1と同様にして18650型の電池を組み立てた。次に、電池を4.1ボルトに充電してから、60℃で1週間保存した。その後、2.5ボルトまで1Aの定電流で放電し、4.1ボルトまで電流を制限した状態で、定電圧充電するサイクルで、電池を21℃においてサイクル試験した。20サイクル毎に、大きさが順次小さくなる一連の放電電流を段階的に印加して、容量損失がより低い放電速度で回復するかどうかを調べた。図2に、この電池の容量対サイクル寿命データを示す。本実施例は、ビフェニル添加剤が5重量%以下ならば、依然としてすぐれたサイクル特性が得られることを示す。

【0056】実施例4

性能の点から潜在的に候補となる添加剤を選別するために、実施例1と同様な一連の18650型電池を作製した。即ち、以下の添加剤(容量%)を配合した電池を作製し、電氣的に状態調節した。0.5%ピロール、0.42%N-メチルピロール、および1%チオフェン。ピロール添加剤を配合した電池は状態調節時に相当大きい

内部短絡を発生したので、十分に充電できなかった。即ち、内部短絡には60mA以上の充電電流を要した。短絡は約3.5ボルトで開始し、電池電圧は約3.7ボルトを越えなかった。N-メチルピロール添加剤を配合した電池については、4.1ボルトに充電した後に、開路状態でモニターした。24時間で、電圧降下は大きく、約3.9ボルトまで降下した。内部短絡は約3.5ボルト以上で発生すると考えられる。チオフェン添加剤を配合した電池については、4.2ボルトまで充電した。開路にした場合、その後1時間で電圧は4.09ボルトまで降下した。これら添加剤は、上記実施例の高電圧電池には向かないと考えられるが(なぜなら、内部短絡が正常な動作電圧範囲で発生するからである)、にもかかわらず、これらは動作充電電圧がより低い非水系電池には好適に使用できる添加剤である。

【0057】以上の説明から、当業者にとっては明らかなように、本発明の精神または範囲から逸脱せずに、本発明を実施する際には、多くの変更や改変が可能である。即ち、本発明の範囲は、特許請求の範囲に定義されている実体に従って解釈すべきである。

【0058】

【発明の効果】再充電可能なリチウム電池において、過充電時において、最大動作電圧以上の電圧において重合して導電性の物質を生成するモノマーを電解質中に添加したので、過充電において最大動作電圧を超えた後は、内部で自動的に放電することとなり、過充電によって蓄積したエネルギーを安全に開放することができる。

【図面の簡単な説明】


【図1】図1は、円筒形の螺旋形リチウムイオン電池の好適な実施態様を示す横断面図である。

【図2】図2は、実施例3の電池に関する容量対サイクル数データを示すグラフである。


【符号の説明】

1…正極箔、2…負極箔、3…セパレータ、4…ジェリーロール、5…電解質、6…正極タブ、7…負極タブ、8、9…絶縁片、10…電池缶、11…ヘッダー、12…ガasket、15…電池

【図1】



【図2】



フロントページの続き

(72)発明者 デビッド スタンレー ウェーンライト
 カナダ ブリティッシュコロンビア州 バ
 ンクーバー ウェスト ファースト アベ
 ニュ 2585

*** NOTICES ***

Japan Patent Office is not responsible for any damages caused by the use of this translation.

1. This document has been translated by computer. So the translation may not reflect the original precisely.
2. **** shows the word which can not be translated.
3. In the drawings, any words are not translated.

CLAIMS

[Claim(s)]

[Claim 1] The lithium cell in which the recharge of the non-drainage system characterized by mixing the monomer additive which generates an internal short circuit at the time of overcharge abuse by carrying out a polymerization by the cell voltage exceeding the maximum operating voltage in the lithium cell which has a non-drainage system electrolyte, and in which a recharge is possible, and generating conductive polymer to the above-mentioned electrolyte is possible.

[Claim 2] The lithium cell in which the recharge of the non-drainage system according to claim 1 characterized by having the overcharge safeguard which protects a cell to overcharge abuse when the maximum operating voltage is exceeded is possible.

[Claim 3] The lithium cell in which the recharge of the non-drainage system according to claim 2 to which resistance is characterized by the bird clapper from a thermistor with the positive temperature coefficient which restricts the charging current by the bird clapper greatly at the time of overcharge of a overcharge safeguard is possible.

[Claim 4] The lithium cell in which the recharge of the non-drainage system according to claim 2 characterized by the bird clapper from gas generating agents other than the aforementioned monomer which generate the gas and pressure which operate this cutting equipment at the time of the internal electric cutting equipment with which a overcharge safeguard operates with predetermined internal pressure, and overcharge is possible.

[Claim 5] The lithium cell in which the recharge of the non-drainage system according to claim 4 characterized by a gas generating agent being Li_2CO_3 is possible.

[Claim 6] The lithium cell in which the recharge of the non-drainage system according to claim 2 characterized by the bird clapper from an electrical circuit means by which a overcharge safeguard restricts the charging current or charge voltage is possible.

[Claim 7] The lithium cell in which the recharge of the non-drainage system according to claim 1 characterized by the mixture of an electrolyte and a monomer additive having less than 5% of the weight of a monomer additive is possible.

[Claim 8] The lithium cell in which the recharge of the non-drainage system according to claim 1 characterized by a monomer additive being an aromatic monomer additive is possible.

[Claim 9] The lithium cell in which the recharge of the non-drainage system according to claim 8 characterized by an aromatic monomer additive being a biphenyl is possible.

[Claim 10] The lithium cell in which the recharge of the non-drainage system according to claim 9 characterized by the mixture of an electrolyte and a monomer additive having 2 - 3% of the weight of a biphenyl additive is possible.

[Claim 11] The lithium cell in which the recharge of the non-drainage system according to claim 8 characterized by being what chosen from the group which an aromatic monomer additive becomes from a pyrrole, N-methyl pyrrole, a thiophene, a furan, Indore, and 3-chloro thiophene is possible.

[Claim 12] The lithium cell in which the recharge of the non-drainage system according to claim 8 characterized by an aromatic monomer additive being a pyrrole, N-methyl pyrrole, or a thiophene is possible.

[Claim 13] The lithium cell in which the recharge of the non-drainage system according to claim 8 characterized by an aromatic monomer additive being a furan, Indore, or 3-chloro thiophene is possible.

[Claim 14] The lithium cell in which the recharge of the non-drainage system according to claim 1 characterized by the maximum operating voltage exceeding 4 volts is possible.

[Claim 15] The lithium cell in which the recharge of the non-drainage system according to claim 1 characterized by being the lithium insertion compound with which a positive electrode is chosen from Li_xCoO_2 , Li_xNiO_2 , or $\text{Li}_x\text{Mn}_2\text{O}_4$ is possible.

[Claim 16] The lithium cell in which the recharge of the non-drainage system according to claim 1 whose negative electrode is a lithium compound negative electrode of a carbonaceous system is possible.

[Claim 17] The lithium cell in which the recharge of the non-drainage system according to claim 1 characterized by the bird clapper from the organic carbonate chosen from the group which an electrolyte solvent becomes from ethylene

carbonate, propylene carbonate, diethyl carbonate, and ethyl methyl carbonate is possible.

[Claim 18] The lithium cell in which the recharge of the non-drainage system according to claim 1 characterized by an electrolytic solute being LiPF_6 or LiBF_4 is possible.

[Claim 19] In the method of making safe the recharge possible lithium cell of the non-drainage system of a overcharge state to future abuse a) by carrying out a polymerization and choosing the monomer additive which forms conductive polymer by the cell voltage exceeding the maximum operating voltage, when the additive which carried out the polymerization at the time of b overcharge generates an internal short circuit How to make safe the recharge possible lithium cell of the non-drainage system of the overcharge state characterized by the bird clapper since the above-mentioned monomer additive of sufficient amount to discharge a cell to a safe charge state is mixed with an electrolyte.

[Claim 20] The method according to claim 19 characterized by the mixture of an electrolyte and a monomer additive having less than 5% of the weight of a monomer additive.

[Claim 21] The method according to claim 19 characterized by having a monomer additive in amount with the sufficient mixture of an electrolyte and a monomer additive generating the internal short circuit which can discharge a cell to a safe charge state within 24 hours.

[Claim 22] The method according to claim 19 characterized by a monomer additive being an aromatic monomer additive.

[Claim 23] The method according to claim 22 characterized by the above-mentioned aromatic monomer additive being a biphenyl.

[Claim 24] The method according to claim 23 characterized by the mixture of an electrolyte and a monomer additive containing 2 - 3% of the weight of a biphenyl additive.

[Claim 25] The method according to claim 22 characterized by being what chosen from the group which the above-mentioned aromatic monomer additive becomes from a pyrrole, N-methyl pyrrole, a thiophene, a furan, Indore, and 3-chloro thiophene.

[Claim 26] The method according to claim 22 characterized by the above-mentioned aromatic monomer additive being a pyrrole, N-methyl pyrrole, or a thiophene. .

[Claim 27] The method according to claim 22 characterized by the above-mentioned aromatic monomer additive being a furan, Indore, or 3-chloro thiophene.

[Claim 28] The way according to claim 19 the above-mentioned maximum operating voltage exceeds 4 volts.

[Translation done.]

*** NOTICES ***

Japan Patent Office is not responsible for any damages caused by the use of this translation.

1. This document has been translated by computer. So the translation may not reflect the original precisely.
2. **** shows the word which can not be translated.
3. In the drawings, any words are not translated.

DETAILED DESCRIPTION

[Detailed Description of the Invention]

[0001]

[The technical field to which invention belongs] this invention relates to the lithium cell in which the recharge of a non-drainage system is possible, and the improvement method of the safety. Especially this invention relates to using a polymerization nature monomer additive as a safety practice of a lithium ion battery to the further abuse after overcharge of a lithium ion battery.

[0002]

[Description of the Prior Art] As a result of calling for the cell in which a recharge with a high energy density is so possible that it is not cutting, the research and development about the lithium cell in which a recharge is possible prosper. If a lithium is used, although high-energy density and a high cell voltage and long storage life will be obtained, the problem (namely, fire) of safety arises. Because, a lithium is because it is a reactant high element. Thus, since a problem is in safety, the lithium cell in which many recharges are possible is not fit for the electrochemical operation and/or use with common size. It is a very small thing (for example, cell whose size is a coin grade), or the primary cell (namely, cell which cannot carry out a recharge) which the cell of the electrochemistry operation which consists of a lithium metal simple substance, or generally uses the negative electrode which consists of a lithium alloy can generally use. However, a safety aspect can use the cell with such an electrochemistry operation in which a large-sized recharge is possible for the military use which is not thought so much as important or the electric supply use in a certain main remote places.

[0003] Recently, the lithium cell which is known as a lithium ion form or a "rocking-chair form" and in which a recharge is possible is marketed increasingly. These cells are the power sources in which the suitable recharge for many consumer electronics uses is possible. Also in the cell (namely, a nickel-Cd cell, an nickel-MH cell, or a plumbic-acid cell) which can be used now and in which the recharge of the conventional form is possible, these cells have the maximum energy density (Wh/L). Furthermore, the operating voltage of a lithium ion form cell is high enough, and can play the role enough by one cell for many electronics uses.

[0004] In the case of a lithium ion form cell, two kinds of different insertion compounds are used to an activity positive electrode and a negative electrode. The lithium cell of 3.6V (average) based on an electrochemistry operation of LiCoO_2 /graphite precursor carbon is marketed now. Moreover, it is LiNiO_2 besides this. The lithium transition-metals oxide compound of a large number including LiMn_2O_4 is also suitable to use it as a positive-electrode material. Moreover, far-reaching carbonaceous system compounds including corks or a pure graphite are also suitable to use it as a negative-electrode material. With the above-mentioned cell product, the non-drainage system electrolyte which consists of solvent mixtures, such as LiBF_4 salt, LiPF_6 salt and ethylene carbonate, propylene carbonate, diethyl carbonate, and ethyl methyl carbonate, is used. Similarly, it is known about the salt and/or solvent which are used for these cells that much alternative exists.

[0005] A lithium ion form cell is weak to a certain kind of abuse, especially overcharge abuse which exceeds the usual operating voltage at the time of a recharge. At the time of overcharge, a superfluous lithium is extracted from a positive electrode and plating arises in a negative electrode corresponding to this depending on superfluous insertion of a lithium and the case. Consequently, the thermal stability of two electrodes deteriorates. When a negative electrode is doped or galvanized with a reactant lithium, it has the inclination for stability to fall, when it is a positive electrode on the other hand, it decomposes and the inclination to generate oxygen becomes strong (270 J. R. Dahn et al., Solid State Ionics, 69 (3-4), pp265- 1994 reference). Moreover, heating of a cell may arise as a result of a surcharge. Many of inputted energy is because it is diffused rather than it is accumulated. When the fall of thermal stability arises with heating of a cell, a thermal overrun dangerous at the time of overcharge arises, and there is a possibility that a fire may break out.

[0006] Generally, the cell charging equipment which consists of a collection object of each lithium ion form cell, and/or the cell pack are equipped with the suitable electrical circuit which prevents a surcharge. However, in order to

cope with emergency failure of a circuit, many makers have built the safety device into each cell itself independently as a means which raises the protection level to overcharge abuse. For example, they are Sony Corp. and Moli as it applies on the U.S. patent specification No. 4943497 and June 25, 1993, respectively and is indicated by the Canada patent application No. 2,099,657 specification exhibited on February 11, 1994. The product which Energy(1990) Limited is manufacturing now is built into the interior in the cutting equipment which operates when the predetermined value which has the internal pressure of a cell at the time of overcharge abuse is exceeded. Moreover, when the predetermined voltage which exists at the time of overcharge is exceeded, in order to generate sufficient gas and to operate cutting equipment, various kinds of gas generating agents (for example, a positive-electrode compound and/or other cell additives) can also be used.

[0007] When internal solid-state capacity is enlarged substantially and it changes into a specific overcharge state, it is made to operate cutting equipment by the fluid pressure in another alternate method (about this, it applies on April 8, 1993 and the Canada patent application No. 2,093,763 specification exhibited on October 9, 1994 has an indication).

[0008] It is also possible to build other overcharge safety devices into lithium cell itself, and to restrict the charging current and/or voltage. In some manufacturers, the thermistor (PTC) of a positive temperature coefficient was incorporated and the charging current at the time of overcharge abuse is restricted partially. In the case of this equipment, by using the combination of heating of a cell and IR heating of PTC, and operating PTC, resistance was enlarged and the charging current is restricted. In principle, also let it be the object of consideration to include the electrical circuit for overcharge protection in the header of each cell itself.

[0009] Additionally, although these preliminary safety devices can be called effective equipment as long as the dangerous problem produced by electric abuse of a surcharge is solved, in the case of the overcharge cell, the charge state is higher than usual. Therefore, the thermal stability of a cell construct is lower than the time of normal, and is in the dangerous state from the time of normal. The cell in such a overcharge state is very weak to mechanical following abuse (for example, destruction) and following mechanical thermal abuse (for example, oven heating). Although it is made to discard if overcharge abuse arises in the case of a large majority of cell after changing into a safe electric discharge state by only discharging by the handicraft, it is desirable to automate this electric discharge.

[0010] However, the cell which has internal electric cutting equipment in an operating state cannot discharge from the outside, cannot remove energy, and cannot make a charge state low. In case the cell in such a cutting state is in such a dangerous state that it is unusual, and is discarded or is poked and hardened, it generates another problem. although it is unhappy, once it cuts, the remaining capacity of such a cell will be lost -- **** (namely, it is in the state where a cell does not operate completely) -- it is considered ** If it is a rash consumer, although it will disassemble a cell or a possibility of losing the temptation treated violently mechanically will become larger than usual at this time, a bird clapper is in an unhappy result. That is, a means to discharge the cell in such a overcharge state automatically and internally is searched for strongly.

[0011] Some meanses to discharge a cell automatically are well-known, and are already proposed. In the case of the drainage system cell of an electrochemistry operation, a recombination reaction arises at the last of charge. This recombination reaction acts effectively, and while charge is continuing, continuous discharge of the cell is carried out. The additive (chemical shuttle) is indicated also about the non-drainage system cell with the same purpose of an electrochemistry operation. A recombination reaction and a chemical shuttle can consider that a cell is what discharges automatically only by the premise of unless the usual maximum operation charge voltage is exceeded.

[0012] A means to generate an internal short circuit on a overcharge cell is also well-known. The metal parts (for example, positive-electrode charge collector) and other additives which are maintained by positive-electrode potential can be rapidly corroded using electrochemical corrosion reaction. In this case, as a result of the corroded component's moving from a positive electrode and galvanizing a negative electrode, a conductive dendrite generates. If corrosion and plating continue, bridge formation of a conductive dendrite forms between a positive electrode and a negative electrode, and a cell can be electrically short-circuited according to bridge formation of this dendrite. In corrosion reaction, cell capacity is hardly consumed in many cases until bridge formation of a dendrite forms. Therefore, corrosion begins above the maximum operating voltage, and when remarkable corrosion arises before a surcharge threatens safety, positive-electrode metal parts and other additives can use it for the above-mentioned purpose suitably. Many alternative of the material which can be used easily exists about the non-drainage system cell of a low battery (for example, about 2 volts). For example, it will be MoliEnergy to the 1980s. Ltd When it is the lithium negative electrode / molybdenum disulfide positive-electrode cell which was being manufactured, while restricting a charge state by the stainless steel in negative-electrode potential and/or nickel metal parts corroding, forming bridge formation of a dendrite, and short-circuiting a cell internally, a cell is protected at the time of overcharge abuse. However, so much alternative does not exist in the non-drainage system cell of higher voltage (for example, about 4 volts). Many of cell metallic materials used now are corroded too much in low potential, in order to secure normal operation of a cell. On the other hand, too much, in low potential, the exotic material which is not corroded is not fully corroded, when

overcharge protection is required. Thus, it cannot use easily [the non-drainage system cell of voltage with both the usual material or a higher exotic material].

[0013] The mechanical means which generate an internal short circuit on a overcharge cell are also examined. For example, one alternative proposed is the same as the above-mentioned electric cutting equipment, if the point incorporating the mechanism in which short circuit connection is made is removed instead of cutting at the time of an operation. However, this alternative is mechanically complicated and a problem is in cost or reliability. If an ideal is said, a means to perform an internal short circuit at the time of overcharge must be reliable, and must be low. [of cost] Moreover, it is made not to localize so that it may be gradual, or the low short circuit of a grade may be generated gradually the optimal, it may distribute to the whole interior of a cell according to a case and the power and the heat which are radiated through a short circuit may not become large suddenly (namely, generating of spot heating). Itself of each condition of these latters is dangerous.

[0014] Using polymerization nature monomer additives, such as a gas generating agent, for a lithium cell is indicated by the Canada patent application No. 2,163,187 specification (JP,9-171840,A) for which these people applied on November 17, 1995 in order to operate internal electric cutting equipment at the time of overcharge. On these specifications, the monomer gas generating agent of a certain kind which generates conductive polymer generates an internal short circuit, and having the operation which discharges a cell after overcharge abuse is also indicated. According to the example, this operation is obtained in fact by the cell which blended the biphenyl additive. The polymer of a biphenyl is conductivity.

[0015] Moreover, using a polymerization nature monomer additive for the Canada patent application No. 2,156,800 specification (JP,9-106835,A) for which these people applied on August 23, 1995 in order to protect between surcharges the lithium cell in which a recharge is possible is indicated. Here, a small amount of polymerization nature additive is mixed to a liquid electrolyte. At the time of overcharge abuse, when an aromatic additive carries out a polymerization on the voltage exceeding the maximum operating voltage of a cell, internal resistance is enlarged and sufficient protection is given.

[0016] It is not indicated directly that it is generally advantageous to whether internal cutting equipment is included in the cell at both the above-mentioned Canada patent application No. 2,163,187 specification and this No. 2,156,800 specification to make the cell itself discharge automatically after overcharge abuse not related. Moreover, when a polymerization is carried out, regardless of whether the monomer additive which generates a conductive polymer is a gas generating agent, or internal resistance of a cell is enlarged considerably, there is no indication direct also about it being advantageous to use a monomer additive.

[0017] A polymerization is carried out electrochemically fundamentally, and some aromatic compounds which can generate conductive polymer are already used for the electrolyte solvent mixture as an electrolyte solvent additive of a salt and/or the non-drainage system lithium cell in which a recharge of a certain kind is possible, in order to extend a cycle life. In JP,61-230276,A, improving cycle efficiency is checked about the lithium metal which the cell for laboratory tests which uses the electrolyte which consists of a furan (aromatic heterocycle) solvent additive galvanized. Moreover, a negative electrode is made into a polyacetylene, a positive electrode is set to TiS₂ at JP,61-147475,A, and except that the cell which used the electrolyte which consists of a thiophene solvent additive does not use an additive, excelling in a cycle property is shown in comparison with the same cell. However, about the operation in the potential safety aspect obtained from the electrochemical polymerization nature of an additive, anything does not have an indication in these official reports. moreover, it is not clear whether the actual embodiment in these official reports has the operation in a safety aspect actually at the time of overcharge abuse (namely, other operations produced at the time of overcharge prevent polymerization nature -- and/or, an internal short circuit does not arise as a result of a polymerization -- a thing)

[0018]

[Problem(s) to be Solved by the Invention] Let it be a technical problem for this invention to discharge the cell capacity charged after overcharge abuse inside in the lithium cell in which the recharge of a non-drainage system is possible, and to make a cell safe.

[0019]

[Means for Solving the Problem] this invention relates to both method of carrying out internal electric discharge of this cell automatically after overcharge abuse of the non-drainage system lithium cell in which a recharge is possible, and embodiment. (I think that it is generated when a cell is charged to the voltage exceeding the usual maximum operation charge voltage with overcharge abuse in this case) . If a polymerization is carried out, the monomer additive which generates a conductive polymer will be blended with a non-drainage system electrolyte. At the time of overcharge abuse, when this monomer additive carries out a polymerization, an internal short circuit is generated on a cell and this is discharged.

[0020] this invention is effective also to any of a cell without a cell with the need of adding a overcharge safeguard

separately, or its need. For example, although an additional means to secure the safety over electric overcharge abuse may be unnecessary in the case of a low-battery cell, after overcharge, a possibility of threatening safety in the next thermal abuse is also by such low-battery cell. For this reason, this invention is effective, when discharging these low-batteries cell in the low charge state more and making the safety in the next thermal abuse high.

[0021] Similarly, this invention is effective also in the cell equipped with an electrical circuit means of a thermistor (PTC) or others to have a positive temperature coefficient, in order to restrict the charging current or voltage. In the case of such a cell (for example, the controlled speed), it can discharge by the handicraft, and safety can be made high if needed. However, when it sees from a safety aspect, in order to ensure electric discharge, it is desirable to perform this electric discharge automatically and internally. It not only can discharge the cell equipped with PTC of a overcharge state automatically, but in the case of the additive of this inventions, such as a biphenyl, of a certain kind, it can raise an operation of PTC at the time of overcharge by enlarging internal impedance (it being indicated by the aforementioned Canada patent application No. 2,156,800 specification like).

[0022] As for this invention, it is desirable to apply to the lithium cell equipped with the internal electric cutting equipment which operates with a predetermined internal pressure in which a recharge is possible. Like the aforementioned Canada patent application No. 2,163,187, while the monomer additive acted as an activation gas generating agent, when the polymerization of it is carried out, it acts as a monomer which generates an internal short circuit. However, the monomer additive of this invention does not need to be the source of primary of a pressure activation gas, and does not need to be a gas generating agent. It is desirable to use other meanses to operate electric cutting equipment, combining the monomer additive of this invention in the case of such an embodiment. Since an internal short circuit can be generated with the additive of this invention after partial overcharge (namely, after a surcharge stops before the operation of electric cutting equipment), a overcharge cell can be made safe when a overcharge cell is understood that it could discharge and overcharge abuse has arisen by the operation of cutting equipment.

[0023] Generally, the non-drainage system cell in which the recharge of this invention is possible consists of a lithium insertion compound positive electrode, a lithium compound negative electrode (for example, a lithium metal, a lithium alloy, or a lithium insertion compound), and a non-drainage system electrolyte (for example, although it is a liquefied electrolyte, a polyelectrolyte and a plasticization polyelectrolyte are also usable). In the case of a lithium ion battery, as a lithium insertion compound, LiCoO_2 can be used and it is LiNiO_2 . And what was chosen from the group which consists of LiMn_2O_4 can be used. A carbonaceous system insertion compound can be used for a lithium compound negative electrode. As a liquid electrolyte solvent, organic carbonates, such as ethylene carbonate, propylene carbonate, diethyl carbonate, and ethyl methyl carbonate, can be used. As a liquid electrolyte solute, lithium salt, such as LiPF_6 and LiBF_4 , can be used. Especially this invention is suitable for the cell by which the maximum operation charge voltage exceeds 4 volts.

[0024] By the cell of this invention, by carrying out a polymerization by the cell voltage exceeding the maximum operating voltage, conductive polymer is generated and the monomer additive which generates an internal short circuit on a cell is mixed to an electrolyte. About the amount of a monomer additive, the generated polymer actually constructs a bridge in a positive electrode and negative-electrode both, and if not enough to short-circuit a cell, it will not become. It is enough if the amount of a monomer additive is less than 5 % of the weight in the mixture of an electrolyte and a monomer additive. An aromatic additive can be used as a monomer additive. A biphenyl is an especially suitable additive for the lithium ion form cell which has operating voltage in the 4-volt range. A biphenyl is effective if it blends into electrolyte mixture in about 2 - 3% of the weight of an amount.

[0025] An aromatic heterocyclic compound is also suitable as an additive. For example, if a pyrrole, N-methyl pyrrole, a thiophene, etc. carry out a polymerization, an internal short circuit will be generated on a certain kind of cell. Thus, if it says widely, although these additives will be suitable additives potentially, the maximum operation charge voltage of a desirable object cell is less than about 4-volt cell. Additives, such as a furan, Indore, and 3-chloro thiophene, are suitable additives for the potential target for a cell with higher charge voltage of operation. Even if it replaces the chemical group from which it differs in these compounds, it is only thought that it is that the influence of some appears in the polymerization potential of polymer and/or conductivity to generate. that is, these substituted compounds are also suitable -- it reaches and they are/or a desirable additive

[0026] By the method of obtaining an expected result for a certain cell, when the monomer additive which generates conductive polymer by the polymerization by the cell voltage exceeding the maximum operation charge voltage is chosen and a polymerization additive generates an internal short circuit at the time of overcharge abuse, the monomer additive of sufficient amount to discharge a cell automatically to a safe charge state is mixed with an electrolyte. Since both a too quick electric discharge speed and a too slow electric discharge speed have other purposes in an additive desirably, as long as it can discharge a cell in the safe charge state within [in about 24 hours] by the generated internal short circuit, it is desirable to use the additive of the minimum amount. (of course, additives, such as a biphenyl, have

another, effective operation.) For example, cutting equipment is operated or it has the operation which enlarges a cell impedance as indicated by the Canada patent application No. 2,156,800 of the two aforementioned affairs, and the No. 2,163,189 specification.

[0027]

[Embodiments of the Invention] In order to suppress accident to the minimum in the case of a certain energy conservation equipment, it is the last of the use stage and an ideal removes energy in advance of abandonment in advance of a certain processing which overworks a cell by the case. The non-drainage system cell in which a recharge is possible, especially the cell for general consumers are not exceptions, either. The great portion of non-drainage system electrochemistry equipment generally used needs to be protected to superfluous charge. It is because the resultant which is not desirable, and byproduction heat will usually arise when full restoration of the energy is carried out at a cell, if such superfluous charge arises. Although these cells are fully protected to the overcharge itself, if it is worked hard again after that (known as "pile" abuse), they will threaten safety potentially.

[0028] In order to secure safety, depending on the general public's spontaneous action is not desirable. About a cell pack, when the general public dissolves, an external protective device may be removed. Each cell may be overworked in spite of being well-known to the risk at the time of treating such in spite of a warning letter simultaneous. A possibility that any cautions may not have the way of a impossible cell of operation, and it may be treated by the general public is stronger than the cell by which the life remains a little. If automatic electric discharge can be carried out with this point at an electric discharge speed safe after overcharging the impossible cell of operation itself, the need of depending on a consumer is desirably avoidable.

[0029] Generally, a lithium ion form cell has the inclination for the stability over thermal abuse to become low as a charge state increases. In the case of a certain kind of commercial lithium ion type cell, one is the purpose which restricts a cell to a comparatively safe charge state thermally, and upper limit voltage is specified. In comparison with the cell of other form, fundamentally, when such a lithium ion form cell will be in a overcharge state, a possibility that pressure opening and the fire by increase of a cell internal pressure may break out is strong. For this reason, for example, in order to prevent a surcharge, a reliable external circuit is established in a lithium ion form cell and/or a cell pack. However, this external circuit can be removed if a user becomes the mind, and although the rate of breakage is small even in the most reliable circuit, there is a limitation. Therefore, the internal overcharge protective device is chiefly formed in the commercial lithium ion form cell. These equipments are effective in giving protection, even when a metaphor external device is removed or it damages.

[0030] Once an internal overcharge protective device operates in the case of a lithium ion form cell, it will be desirable that it will be in a use impossible state. A overcharge cell continues being thermal or the thing which threatens safety potentially to mechanical abuse until it discharges. [follows] The need that a user intervenes also in a misfortune suitably in order to perform subsequent electric discharge arises frequently. Although based also on a case, a user cannot sometimes even discharge a cell externally. This is applied when internal electric cutting equipment operates. For a user, the cell by which cutting equipment operated is a cell in the state "where it died", and is a cell which cannot discharge from the outside.

[0031] this invention offers a means to discharge a cell automatically after overcharge of a non-drainage system cell, in order to tackle this problem. This is realized by carrying out little combination of the suitable polymerization nature monomer additive for the non-drainage system electrolyte of a cell. What is necessary is to carry out a polymerization on a certain suitable voltage, and just to choose what becomes conductive polymer about this monomer additive. what is necessary is just to choose the monomer in which a significant polymerization does not occur in the normal operating voltage range namely, -- at the time of normal operation of a cell, if it puts in another way If a monomer additive reaches polymerization voltage at the time of overcharge abuse, it will start a polymerization. By sufficient conductive polymer's generating and finally, forming conductive bridge formation in cell inter-electrode, an internal short circuit is generated on a cell and a cell is discharged. When it sees from a safety aspect, before a cell reaches the charge state which is not desirable, it is desirable that conductive bridge formation forms. In this way, if it sets, as long as there will be no start of internal electric discharge, the state which is not desirable as for the above cannot overcharge partially in a cell.

[0032] Therefore, in order for the monomer additive to be effective, it is necessary to satisfy some conditions simultaneously. That is, a polymerization must be carried out electrochemically and bridge formation of conductive polymer must be able to be rather formed on specific voltage. Moreover, except for this point, combination of an additive must not have a bad influence on a cell performance. In principle, although many monomers can be used, especially an aromatic monomer is suitable. It is because polymerization potential is in the range suitable for this use and also conductive polymer generates by polymerization reaction. Furthermore, even when it is little, there is also an advantage that conformity is shown in the chemical action of a lithium cell in many cases in an aromatic compound.

[0033] 1979 Let R.J.Fessenden et al. published from Willard Grant Press be an author. "Organic Chemistry" it argues --

as -- a term -- the cyclic compound substantially stabilized by the delocalization of a pi electron as it is "aromatic" is pointed out. Such a compound has a ring structure or the planar structure, and each atom of a ring has the p orbital which intersects perpendicularly to the flat surface of a ring (sp² hybrid state). Moreover, a 4n+2 pi electron (n is an integer) must exist in a ring system (HÜCKEL rule). Terms "a heterocycle formula" are (The Condensed Chemical Dictionary, the 9th edition, G.G.Hawley, Van Nostrand Reinhold, refer to 1977), and a thing that usually points out the ring closure structure of 5 members or 6 members. In this case, the atoms beyond one or it in a ring are elements other than carbon (for example, sulfur, oxygen, and nitrogen).

[0034] A common aromatic compound has the ring structure which can carry out the polymerization of this invention electrochemically very easily in the voltage range in the target use. If a heteroatom exists in the ring structure in the case of many aromatic heterocyclic compounds, since it will be rich [in an electron] of the carbon atom which adjoins this, ring breakage arises simply and a polymerization arises in these positions. In the case of other unsaturation cyclic compounds, an electrochemistry polymerization is not carried out that simply.

[0035] As an aromatic compound which generates conductive polymer, a biphenyl, a pyrrole, Indole, a thiophene, furans, these derivatives, etc. can be used, for example. (It re-recorded from Electrochemistry in Organic Synthesis, J.Volke&F.Liska, Springer-Verlag, and 1994) The conductivity of the formed polymer film is shown with the oxidation potential to the saturated calomel electrode of some monomers in Table 1.

[0036]

[Table 1]

Compound Oxidation potential (V pair S C E) Conductivity (Scm⁻¹)

Pyrrole +0.8 30-100 Indole +0.8 5x10⁻³-10⁻² Thiophene +0.9 10-100 Furan +1.85 10-80 [0037] In addition, a certain grade depends for polymerization potential on other electrolyte components used for an electrode and electrochemical equipment (cell). Although the value indicated by reference suggests the compound with which this invention may serve as a candidate in the target use, in an actual cell environment, a polymerization advances in a different form a little. That is, although the cell maximum operation charge voltage is exceeded, under actual cell conditions, the compound which carries out a polymerization on the voltage which is less than the overcharge voltage which becomes that to which a cell threatens safety comparatively is suitable. In addition, about a polymerization, sufficient rate of polymerization to form sufficient bridge formation by polymer sufficient by the time of being needed is required.

[0038] A certain grade depends for conductivity required for a polymer on an electrochemistry operation and cell design of the gestalt of a polymer, and a cell. Resistance is considered to be a low rather than bridge formation with conductive bridge formation of precise polymer strong [fiber nature]. When it is a cell with a small electrode area with thick and/or separator, conductive high polymer is more nearly required than a cell with a large electrode area with thin and/or separator. It is because a bridge formation object is shortened and a cross sectional area can be enlarged, in order to obtain the same real resistance in the case of the high polymer of resistance. At the end, required internal resistance depends for the safety standard to a cell voltage, a specific capacity, and a specific charge state.

[0039] What is necessary is generally, just to use the monomer additive of the minimum amount which obtains an expected internal short circuit from the purpose of this invention. When an additive is first used [1st] for it in a superfluous amount to an electrode as opposed to a lithium even if an additive is inactive although it must be inactive comparatively (that is, it does not react with a lithium or does not insert in an electrode), it may have a bad influence on a cell performance characteristic (for example, increase in a cell impedance). If the example of representation mentions, if an additive exists in an electrolyte by several % of the weight or number capacity %, in this invention, it is enough. Similarly, a part depends on an electrochemistry operation and cell design of a cell, and a part depends for an actually usable initial complement on a monomer property.

[0040] In case an additive is chosen according to a use therefore, it is necessary to satisfy some criteria. Although the tolerance which satisfies these criteria is comparatively wide, in order to know the conformity of the specific additive which serves as a candidate to a predetermined cell use, it is necessary to conduct some experiments without the direct relation to invention. These experiments have the overcharge examination of the trial production cell which contains the additive which serves as a candidate in a different amount. After choosing in case an usable quantity of an additive is chosen externally or, in order to examine the bad influence to a performance completely, it is necessary to perform a performance test of a certain kind about a trial production cell. Such a trial production cell is in this contractor's range and ability range, and does not independently need invention nature.

[0041] It found out that the additive for the lithium ion form cell product marketed for consumer electronics with an especially suitable artificer etc, was a biphenyl. Separator is thin (about 25 micrometers) and the electrode surface area of these cells is large (100cm² of divisors 2). Usually about cell capacity, they are 1Ah or more than it. Moreover, the normal maximum operation charge voltage is about 4.2V. Between this 4.2V and about 5 V, the danger of a cell becomes comparatively strong. If electric discharge arises above C rate, several% of biphenyl will fully carry out a polymerization, will form conductive bridge formation, and will discharge a cell to a safe charge state within [in 24

hours]. it is indicated by the Canada patent application No. 2,156,800 specification -- as -- such cell environment -- setting -- a biphenyl additive -- Li/Li^+ I think that it receives and a polymerization is carried out by 4.70V -- having -- little use -- a cell performance -- an owner -- it does not have a meaningless bad influence On these specifications, it is supposed potentially [others, such as 3-chloro thiophene and a furan,] that a suitable additive is also usable.

[0042] According to the example mentioned later, it became clear that it is suitable for the non-drainage system cell in which other additives have low operation charge voltage (namely, less than [4.2V]) more. There are N-methyl pyrrole and a thiophene in these additives, and voltage is considered to be suitable more by the low cell. It is because an internal short circuit occurs on low voltage too much by the typical cell. Although the above-mentioned additive and other additives (namely, a substituted compound and its derivative) with a close relation are the same, a slightly different property is shown, and it is thought that it is so the desirable alternative in a use of a certain kind.

[0043] If existence of an additive is set aside, the composition of this invention cell is the same as that of a cell conventionally. What is necessary is just generally, to only mix an usable quantity of an additive to a bulk electrolyte, when [suitable] it is at the time of a cell assembly. Needless to say, according to the difference among the properties (for example, vapor pressure, toxicity, etc.) of a bulk electrolyte or an additive, it needs to be changed on some operations. The lithium cell in which the recharge of the non-drainage system marketed is possible can have various kinds of configurations (namely, a prismatic cell and a small coin form cell), and can use the component from which many differ. (For example, although such an additive probably seldom moves in a macromolecule system electrolyte, the same property is realized when the cell which consists of a solid-state polyelectrolyte also blends such an additive). About the desirable composition of a lithium ion form cell product, a cross-sectional view is shown in drawing 1 as a conventional spiral cell. The microporosity polyolefine sheet 3 of two sheets which acts as the positive-electrode foil 1, the negative-electrode foil 2, and separator is made into a spiral volume, and the jelly roll 4 is produced.

[0044] To a thin aluminum foil, if positive-electrode foils are suitable powdered (grain size is about 10 micrometers) positive-electrode material, such as a lithiation transition-metals oxide, and a request, they will apply and produce the mixture which consists of other powdered positive-electrode material, binders, and conductive diluents. In the example of representation of the method of application, after dissolving a binder in suitable liquid support first, in addition to this solution, other powdered solid-state components are used, and a slurry is produced. Next, a slurry is uniformly applied to a base foil. Then, evaporation removal of the support solvent is carried out. After in many cases doing in this way and carrying out application processing of the both sides of an aluminum foil base, calender processing of the positive-electrode foil is carried out.

[0045] In the case of a negative-electrode foil, a carbonaceous system insertion compound [that it is powdered instead of positive-electrode material (grain size is about 10 micrometers)] is used, and it produces it like the above except usually using copper foil thin instead of aluminum. Moreover, width of face of a negative-electrode foil is slightly made larger than the width of face of a positive-electrode foil, and it is made for a negative-electrode foil to always counter a positive-electrode foil certainly.

[0046] The jelly roll 4 is inserted in the usual cell can 10. A header 11 and a gasket 12 are used and a cell 15 is sealed. The superficies of a battery case 10 are used as a negative terminal by using the superficies of a header 11 as a positive terminal. The positive-electrode tab 6 and the negative-electrode tab 7 are connected suitably, and an external terminal is connected with an internal electrode. The suitable insulating pieces 8 and 9 can be inserted, and the possibility of an internal short circuit can be prevented beforehand. before carrying out the crimp of the header 11 to the cell can 10 and sealing a cell -- an electrolyte 5 -- in addition, the jelly roll 4 -- fine -- a hole -- it is filled up with space In the case of the cell of this invention, an usable quantity of a monomer additive is further blended with an electrolyte 5. For example, equipments beyond one or it, such as interior of pressure operation formula electric cutting equipment, and a positive heat coefficient thermistor (PTC), a positive overcharge protective device, are formed, and a cell is protected from the electric abuse by the surcharge. Moreover, since it is another, you may also build a safety device into a header. Usually, you may incorporate the safe mouth which explodes when a superfluous pressure is accumulated on a cell.

[0047] Moreover, by the cell shown in drawing 1, the internal electric cutting equipment same with being shown in the Canada patent application No. 2,099,657 specification is built into a header 11. This cutting equipment can operate by gas generating agents, such as Li_2CO_3 . Although this gas generating agent can be used also as a polymerization nature additive which generates) and an internal short circuit as shown in the (above-mentioned Canada patent application No. 2,163,187 specification, this is not necessarily required. Or in order to use the polymerization nature additive which does not generate a gas at the time of the overcharge which generates an internal short circuit or to operate cutting equipment, it is also desirable to use another means (for example, means currently indicated by the above-mentioned Canada patent application No. 2,093,763 specification). Since the monomer additive which carries out a polymerization by fracture of double combination does not generate a gas-like by-product, in such a case, it is suitable.

[0048] Hereafter, although explanation is continued only for the purpose of instantiation, any meanings do not restrict this invention. Although a limit of the theory is not received, the polymerization of an additive is produced in a positive

electrode and it is thought that polymer is generated on a positive-electrode front face. The additive included in the electrolyte continues movement toward a positive electrode, it contacts and carries out a polymerization to a positive electrode, and the sludge which finally contacts a negative electrode through separator grows. Thus, conductive bridge formation can be formed. In the case of a typical lithium ion form cell, each electrode is thin and touches the microporosity separator of low capacity physically. Therefore, a comparatively little monomer is also considered that an expected internal short circuit is realizable.

[0049]

[Example] Hereafter, although an example explains some modes of this invention, these examples do not restrict this invention in any meanings. As it already explained and was shown in drawing 1, the cylindrical shape cell of 18650 sizes (for a diameter, at 18mm, height is 65mm) was produced for the whole. A positive electrode 1 is LiCoO₂ to the both sides of the thin aluminum foil whose length width of face is about 5.4cm, and is about 49.5cm. The mixture which consists of powder, a carbonaceous system conductivity diluent, and a polyvinylidene-fluoride (PVDF) binder was applied uniformly, and was produced. Coverages were about 47 mg/cm². About the negative electrode 2, although length was the same as the positive electrode, width of face applied uniformly the mixture which becomes thin copper foil large 3mm from nodular-graphite powder, carbon black SuperS (trademark of Ensagri), and a polyvinylidene-fluoride (PVDF) binder (it is used to nodular-graphite powder in about 2 % of the weight and about 10% of the weight of an amount, respectively), and produced it. a coverage -- about 23 mg/cm² it was. Separator 3 was produced using the microporosity polypropylene film. As an electrolyte 5, the EC/PC/DEC capacity factor used the solution of lithium salt which dissolved in the solvent mixture which consists of the ethylene carbonate (EC) of 30/20/50, propylene carbonate (PC), and diethyl carbonate (DEC). About 5ml electrolyte was used for each cell.

[0050] LiBF₄ of example 11.5M It was used and two 18650 type cells were assembled as mentioned above. However, an additive was not used for the 1st cell for comparison, but 2% of the weight of the biphenyl additive was blended with the 2nd this invention cell at the electrolyte. (In addition, since a biphenyl is a solid-state at a room temperature, it is quantified not by capacity but by the weight for convenience). A pressure opening mouth and internal electric cutting equipment were formed in these cells as indicated by the above-mentioned Canada patent application No. 2,099,657 specification. Conditioning of the cell was first carried out at 21 degrees C by carrying out a recharge to charge, electric discharge, and a degree to the normal maximum operation charge voltage of 4.1v.

[0051] The feeder system with 10v serviceability was used, and the overcharge abuse examination of the two above-mentioned cells was carried out with the ambient temperature of 21 degrees C. The cell was partially overcharged by 3A and 3.6A for 12 minutes (sufficient time to be able to make the charge state of a cell high intentionally, without internal electric cutting equipment operating), respectively. Next, it acted as the monitor of the cell for about 19 hours. In the meantime, the voltage of the 1st cell was stable in about 4.5v. The voltage of the 2nd cell descended continuously and became about 4.05v 19 hours after. When the presser-foot-stitch-tongue penetration test was performed per each cell, the internal short circuit arose. The pressure opening mouth operated, and exploded and carried out flaming of the 1st cell for comparison. Since itself fully discharged in comparison with the cell for comparison in spite of having suited the overcharge state highly slightly first, the cell by which this example blended the biphenyl additive shows that the safety at the time of next mechanical abuse was remarkably high.

[0052] LiPF₆ of 1M which blended the biphenyl additive of two a2.5 % of the weight of examples Conditioning of the ten 18650 type cells was assembled and carried out like the example 1 except having used the electrolytic solution. The cell was overcharged by 21 degrees C and 3.6A until internal electric cutting equipment operated. (In this example, the biphenyl operated cutting equipment as it acted also as a gas generating agent and was indicated by the above-mentioned Canada patent No. 2,163,187 specification). After saving the cell for 24 hours, the presser-foot-stitch-tongue penetration test was performed. There was also no opening of the pressure opening mouth of a cell, and there was also no combustion. The maximum surface temperature recorded by the cell into the presser-foot-stitch-tongue penetration test was 33 degrees C.

[0053] b) Except for the point which used neither an additive nor internal cutting equipment, conditioning of the three 18650 type cells was assembled and carried out like a. However, the cell was protected to overcharge abuse by building PTC equipment into the header of these cells, and restricting the charging current. these cells were overcharged by 21 degrees C and 3.6A until PTC operated, and PTC fully heated and went up rapidly [resistance] and remarkably namely, -- There was also no opening of a pressure opening mouth and there was also no combustion. Next, after saving the cell in the state of the open circuit for 24 hours, the presser-foot-stitch-tongue penetration test was carried out. One of these three cells had intense cell leakage, and it carried out flaming.

[0054] c) Except for the point which used LiBF₄ electrolytic solution of 1.5M which does not blend an additive, conditioning of the six 18650 type cells was assembled and carried out like the above. Each cell was constituted so that internal electric cutting equipment might carry out a fluid-pressure operation by the increase in the internal solid-state capacity in a certain specific overcharge state as indicated by the above-mentioned Canada patent application No.

2,093,763 specification. These cells were overcharged by 21 degrees C and 3.6A until internal electric cutting equipment operated. There was also no cell leakage and there was also no combustion. Next, after saving the cell for 24 hours, the presser-foot-stitch-tongue penetration test was carried out. Five of these six cells had intense cell leakage, and they carried out flaming. this example blends an additive within 24 hours after overcharge, and although it has either cutting equipment or PTC in the case of the cell equipped with cutting equipment, an additive shows that the safety in the next mechanical abuse became remarkably high compared with the cell for comparison which has not been blended.

[0055] The 18650 type cell was assembled like the example 1 except having blended the biphenyl additive of 35 % of the weight of examples with the electrolyte. Next, the cell was saved for one week at 60 degrees C, after charging 4.1v. Then, it discharged by the constant current of 1A to 2.5v, and the cycle examination of the cell was carried out in 21 degrees C in the cycle which carries out constant-potential charge where current is restricted to 4.1v. It investigated whether a series of discharge currents to which a size becomes small one by one would be impressed gradually every 20 cycles, and it would recover at electric discharge speed with lower capacity loss. The capacity pair cycle-life data of this cell are shown in drawing 2. this example shows that the cycle property which was still excellent is acquired, if a biphenyl additive becomes 5 or less % of the weight.

[0056] In order to sort out the additive which serves as a candidate from the point of example 4 performance potentially, the same 18650 type cells of a series of as an example 1 were produced. That is, the cell which blended the following additives (capacity %) was produced, and conditioning was carried out electrically. 0.5% pyrrole, a 0.42%N-methyl pyrrole, and 1% thiophene. Since the cell which blended the pyrrole additive generated the considerable large internal short circuit at the time of conditioning, it has not fully charged. That is, the internal short circuit took the charging current 60mA or more. Starting the short circuit by about 3.5v, the cell voltage did not exceed about 3.7v. About the cell which blended N-methyl pyrrole additive, after charging 4.1v, it acted as the monitor in the state of the open circuit. The voltage drop was large and descended to about 3.9v in 24 hours. It is thought that an internal short circuit is generated in about 3.5v or more. About the cell which blended the thiophene additive, it charged to 4.2v. When it was made an open circuit, voltage descended to 4.09v after that in 1 hour. Although it is thought that these additives do not turn to the high-voltage cell of the above-mentioned example (it is because it generates in the operating voltage range with a normal internal short circuit) nevertheless, these are the additives which can be used suitable for a non-drainage system cell with lower charge voltage of operation.

[0057] For this contractor from the above explanation, in case this invention is carried out without deviating from the soul or the range of this invention so that clearly, many change and alterations are possible. That is, according to the substance defined as the claim, you should interpret the range of this invention.

[0058]

[Effect of the Invention] In the lithium cell in which a recharge is possible, in the time of overcharge, since the monomer which carries out a polymerization in the voltage more than the maximum operating voltage, and generates the conductive matter was added in the electrolyte, after exceeding the maximum operating voltage in a surcharge, it can discharge automatically inside and the energy accumulated by the surcharge can be opened safely.

[Translation done.]